Technical Data Sheet





Product Information

Composition	Construction	Mat Size	Sq. ft. per Mat	Edge Finish	Available Thickness	Manufactured
Recycled Rubber	Mats	38" x 38"	10.02	Square	4mm, 5mm, 6mm (Square only)	North America
Synthetic Rubber	manufactured in block form	37" x 37"	9.5	Interlocking	7mm, 8mm, 9mm, 10mm (Both edge finishes)	
Polyurethane Binder					Custom thicknesses available	

Installation

Edge Finish	Installation Type	Layout
Square	DinoGrip adhesive	Ashlar/Brick pattern
Interlocking	Loose lay	Ashlar/Brick pattern

Maintenance

Cleaner	Cleaning	Cleaning Method
DinoClean	Vacuum or sweep	Microfiber map Auto Scrubber

Product

Homogeneous, no color wear

High Density, Low Porosity

Durable product, ease of maintenance



Sustainability

Certification Attribute	Standard	3rd party Certification/Certifier	
Low-Emitting Material	CDPH/EHLB v1.2-2017 (California Section 01350)	#SCS-FS-02144	
LEED Scorecard	MR2.2, MR4, MR5, EQ4.1, EQ4.3, ID1.1		
Environmental Product Declaration (EPD)	ISO 14025:2006 and ISO 21930:2007	SCS-EPD-03589	

Performance	Standard	Requirement	Performance vs. Requirements		
TVOC Range	CDPH/EHLB v1.2-2017 (California Section 01350)	<0.5 mg/m³	Pass		
Low Emitting Adhesives	SCAQMD Rule #1168	Less than 50 g/L	Pass, 37 g/L		
	Evo 50: 56.57% Post-Consumer, 3.31% Pc	Post-Industrial, 59.87% Total Recycled Content			
	Evo 60: 41.91% Post-Consumer, 4.72% Post-Industrial, 46.63% Total Recycled Content				
Recycled Content	I EVO /II: 19 6 / % POST-L ONSILMER / 11% POST-INGUISTRIAL /6 6 / % LOTAL RECVCIED L'ONTENT				
	Evo 80: 16.27% Post-Consumer, 7.35% Post-Industrial, 23.62% Total Recycled Content				
	Evo 90: 13.43% Post-Consumer, 7.65% Post-Industrial, 21.07% Total Recycled Content				



Technical Data Sheet





Testing

resurig		
Description	Test Method	Over 50% Color
Accelerated Floor Trafficking		None
Sound Absorption / Noise Reduction Coefficient	ASTM C423	SAA - 0.06
Sound Absorption / Noise Reduction Coefficient	ASTIVI C425	NRC - 0.05
Taber Abrasion	ASTM C501	Weight Loss 2.85 grams (4.0%)
Compression Set Under Force	ASTM D395B	94.7% Recovered; 5.3% Unrecovered
		Breaking Load: 73.7lbs - 119.5 lbs
Breaking Load / Elongation / Tenacity	ASTM D412	Elongation: 69.9% - 117.6%
		Tenacity: 186.1 lbs/square inch - 292.2 lbs/square inch
Static Coefficient of Friction	ASTM D2047	Dry 0.85; Wet 1.01
Hardness Shore A Durometer	ASTM D2240	59 - 62
Density Foam Test	ASTM D3676	78.3 lbs/cu. ft.
Impact Sound Transmission (with Plenum)	ASTM E492	4mm IIC 56; 8mm IIC 59
		CRF 0.23 watts/square cm (4mm 80% EPDM)
Critical Radiant Flux	ASTM E648	CRF 0.22 watts/square cm (6mm 75% EPDM)
		CRF 0.37 watts/square cm (6mm High Color)
Catal Dadie at Flor (4F at a large)	ASTM E648	CRF 0.59 watts/square cm (4mm 70% EPDM)
Critical Radiant Flux (15 min burn)	(NY)	CRF 0.58 watts/square cm (4mm 80% EPDM)
Flexibility	ASTM F137	6mm Mandrel PASS
Electrical Resistance - Surface to Ground	ASTM F150	1.9 x 10 ¹¹ Ohms (average)
Electrical Resistance - Surface to Surface	ASTM F150	3.9 x 10 ¹¹ Ohms (average)
Chemical Resistance	ASTM F925	No Change
Chemical Resistance - Liquid Nitrogen (5 min & 24 hr)	ASTM F925	No Change
Static Load (1000 lbs)	ASTM F970	0.042 inch (10.6%) residual compression
Short Term and Residual Indentation (@ 140 lbs)	ASTM F1914	-0.030 Inch (9.0%) Residual Indentation
Mildew Resistance	ASTM G21	No Mildew After 28 Days

Warranty

10-year Limited Commercial Warranty when installed in accordance with Dinoflex's Installation Guidelines.

